
# **Technical Data Sheet**

















## Airtop UC

### Super premium synthetic compressor fluid

#### Description

Airtop UC fluids are 100% synthetic with good biodegradability and are environmentally neutral. They also exhibit much better oxidation and thermal stability, longer fluid life, and mix perfectly with OEM polyglycols. This ability to mix with PAG's means flushing of compressors is not necessary to change to Matrix Airtop UC. This provides the added benefit of allowing topping off of

compressors containing polyglycol fluids until scheduled change intervals.

#### **Benefits**

- Outstanding oxidation stability
- High flash & auto-ignition points
- Excellent coolant properties
- Very long life fluid
- Excellent materials compatibility
- Excellent rust & corrosion control
- Very good separation from water

#### Typical performance data

	Test method	32	46	50
Viscosity index	ASTM D2270	134	132	162
Viscosity @ 40 °C, cSt	ASTM D445	33.0	46.0	50.1
Viscosity @ 100 °C, cSt	ASTM D445	6.1	7.6	9.0
Viscosity @ 37 °C, SUS	ASTM D445	155	209	233
Viscosity @ 100 °C, SUS	ASTM D445	46.2	50.4	55.8
Flash point, °C	ASTM D92	232	240	242
Auto ignition point, °C	ASTM D2155	377	383	384
Pour point, °C	ASTM D97	-40	-38	-37
4-ball wear test	ASTM D4172			
<ul> <li>Wear scar, 40 kg, 1200</li> <li>RPM, 167°C 1 hr, dia mm</li> <li>Welding load, kg</li> </ul>		0.41 100	0.41 100	0.41 100
Copper corrosion, 24 hr	ASTM D130	1a	1a	1a
Demulsibility, 130 °C, 30 min	ASTM D1401	40/39/1	40/39/1	40/39/1

All performance data on this Technical Data Sheet are indicative only and can vary during production Matrix Specialty Lubricants BV - info@lubes-portal.com - www.lubes-portal.com

19/03/2010 Version 1 Page 1 of 1